

Brilliant Green FFBN Liquid	Olive Green BN Liquid	Olive Green MWN Liquid	Grey 3BN Liquid	Grey NC Liquid	Olive TN Liquid	Olive RN Liquid	Black GRN Liquid	Black BRG 2023 Liquid	Black BRN Liquid
30	75	70	85	110	70	60	40	40	35
7	7	7	6-7	7-8	7	7	5-6	7	7
7	7	6-7	6-7	7	7	7	4	7	7
4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
4-5	4	4-5	4-5	4-5	4-5	4-5	4	4-5	4-5
6	6	7	6	7	6-7	5-6	4	6-7	6-7
4	4	4-5	4	4-5	4-5	4	4	4-5	4-5
4-5	4-5	4-5	4	4-5	4	4	4	4-5	4-5
4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4
4	4	4-5	4	4-5	4	4	3-4	4-5	4-5
4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4	4
4	4	4-5	4	4-5	4	4	3-4	4	4
2-3B	4	3-4B	4Y	4	4Y	3-4R	4	4	4
4-5	4-5	4-5	4-5	4-5	4-5	4	4	4	4
4	4	4-5	4	4	4	3-4G	3-4	4	4
4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5
4	4	4	4	4	4	3-4	3-4	4	4
4-5	4-5	4-5	4	4	4-5	4	4	4	4
4-5	4-5	4-5	4	4-5	4-5	4	4	4	4
4-5	4-5	4-5	4-5	4-5	4-5	4-5	3-4	4-5	4-5
4-5	4-5	3-4	4	4-5	4-5	4-5	3-4	4	4



These information, suggestion and examples are based on our current laboratory and practical experience and composed for purpose of leading users about our products and not considered legally binding.

Bu kartelada sunulan bilgi, örnek ve öneriler; uygulayıcılara ürünlerimiz hakkında yol göstermek amacıyla güncellenen laboratuvar ve işletme deneyimlerimize dayanarak oluşturulmuş olup hukuki bağlayıcı bir garanti ifade etmez.

**Setas Kimya Sanayi A.Ş.**





























Çerkezköy Organize Sanayi Bölgesi Karaağaç Mah.  
9.Sok. No:3, 59520 Kapaklı, Tekirdağ, Türkiye  
T. +90 282 758 18 23 pbx F. +90 282 758 18 32  
www.setas.com.tr

KAR-R 04  
Rev. 0, 02/2017

# Setanthren®

Vat dyes for cellulosic fibre  
Selülozik elyaf için vat boyalar



Setanthren® liquid			Yellow GCN Liquid	Yellow F3GCN Liquid	Yellow 5GFN Liquid	Golden Yellow RKN Liquid	Yellow 3RN Liquid		Orange RRTSN Liquid	Brilliant Orange GRN Liquid	Brilliant Red RN Liquid	Red FBBN Liquid	Rubine RN Liquid	Scarlet GGN Liquid	Bordeaux RRN Liquid	Brilliant Red LGGN Liquid	Violet RRDN Liquid	Red Violet RRN Liquid	Violet BN Liquid	Blue RSN Liquid		Brilliant Indigo 4BDN Liquid	Blue BC Liquid	Blue CLFN Liquid	Navy Blue BRR Liquid	Dark Blue DBN Liquid	Navy Blue BRG Liquid	Navy Blue BGN Liquid	Brown BRN Liquid	Brown RRN Liquid	Brown RRDN Liquid	Brown HRN Liquid	
Full shade / Kök																																	
Stock Color / Kök g/kg			40	80	35	15	35		35	30	50	40	20	80	40	30	25	25	25	45		40	45	55	40	35	40	35	60	60	60	60	
Fastness / Haslıklar																																	
Light / Işık %	ISO 105-B02	1/1 SD	4-5	6-7	5-6	6	7		6	6	6	7	6-7	7	6-7	5	6	5-6	6-7	7		5	7	7	6-7	7	6-7	7	7	7	7	5-6	7-8
		1/12 SD	3	5-6	4	5	6		4	5	4	5	5	5-6	5-6	4-5	4-5	4-5	5-6	6		3	6-7	6	5	6-7	5	6-7	7	7	3-4	6	
Perspiration light / Ter Işık	ISO 105-B07	Acidic	4	4-5	4	4	4		4-5	4	3-4	4	4-5	4	4-5	4	4	4	4-5	4-5		3-4	4-5	4-5	4	4	4	4	4-5	4-5	4	4	
		Alkaline	3-4	4-5	4	4	4		4-5	4	3-4	4	4-5	4	4-5	4	4	4	4	4-5	4-5		3-4	4-5	4	4	4	4	4	4-5	4-5	3-4	4
Weathering / Hava şartlarında ışık	ISO 105-B04	1/1 SD	3	7	5-6	3-4	6		4	4	3	5	5-6	4-5	4-5	4	3	3	4	6		3	6-7	7	5	6	5-6	6	6-7	6-7	3	6	
Washing / Yıkama	ISO 105-C09	C	4-5	4-5	4-5	4-5	4		4	4	4	4-5	4	4-5	4-5	4-5	4	4	4	4		4	4	4	4	4	4	4	4-5	4-5	4-5	4	4
		CO	4-5	4-5	4-5	4-5	4-5		4-5	4-5	4-5	4	4-5	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5		4-5	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5	4-5	4-5
	ISO 105-C06:E1S (1x)	C	4-5	4-5	4-5	4-5	4-5		4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4	4-5	4-5		4-5	4-5	4-5	4	4	4	4	4-5	4-5	4	4-5	4-5
		CO	4-5	4-5	4-5	4-5	4-5		4-5	4-5	4-5	4	4-5	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5		4-5	4-5	4-5	4-5	4-5	4	4	4-5	4-5	4-5	4-5
Industrial laundering / Endüstriyel yıkama	ISO 15797	C	4-5	4-5	4-5	4-5	4-5		4	4	4-5	4	4	4-5	4-5	4-5	4	4	4	4		4	4	4	4	4	4	4	4	4-5	4	4-5	4
Hot Pressing dry / Sıcak pres	ISO 105-X11 immediately / anında	C	4	4-5	4-5	4-5	4		4	4-5	4	4-5	4	4Y	4Y	4	4	4	3-4	4		3-4	4	4-5	4	4	4	4	4	4	4	4	4
		ISO 105-X11 after 4 hours / 4 saat sonunda	C	4-5	4-5	4-5	4-5	4-5		4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4	4	4-5		4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5	4-5
Mercerizing 5 min / Merserize 5 dk.	ISO 105-X04	C	3-4	4R	3-4R	4	4-5		4	4	3-4Y	4Y	4	4-5	4-5	4Y	3-4R	3-4	3-4	4		3-4R	4-5	4	4	3-4R	4	4R	4G	4	4-5	4	
		CO	4-5	4-5	4-5	4-5	4-5		4-5	4	4	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5		4-5	4-5	4-5	4	4-5	4	4-5	4-5	4-5	4-5	4-5	
Dry cleaning / Kuru temizleme	ISO 105-D01	C	4-5	4-5	4-5	4-5	4-5		4-5	4-5	4	4-5	4-5	4-5	4-5	4-5	4	4	4	4-5		4	4	4-5	3	4-5	3	4-5	4-5	4-5	4-5	4	
Chlorine washing / Klorlu yıkama	AATCC 61 4A (71±2 °C)	C	4-5	4-5	4-5	3-4	4-5		4-5	4-5	4	4-5	4	4	4	4-5	4	4	4	2-3G		3	3-4	4	3-4	4	3	4	4	4-5	3-4	3-4	
	AATCC 61 5A (49±2 °C)	C	4-5	4-5	4-5	4	4-5		4-5	4-5	4-5	4-5	4-5	4-5	4	4-5	4-5	4-5	4-5	4-5		3G	4	4-5	4-5	4	4-5	3-4	4-5	4-5	4-5	4	4
Peroxide bleaching / Peroksit ağartma	ISO 105 N02 (Bath1 / Banyo1)	C	4	4	4-5	4	4-5		4-5	4-5	4	4-5	4-5	4-5	4	4	4	4	4-5	4-5		4-5	4-5	4-5	4	4-5	4	4-5	4	4	4-5	4-5	
		CO	4-5	4-5	4-5	4-5	4-5		4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5		4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4	4-5
Hypochlorite bleaching / Hipoklorit ağartma	ISO 105-N01	C	4-5	4-5	4-5	4-5	4-5		4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5	4-5		1-2	4	4-5	4-5	4	4-5	4	4-5	4-5	4-5	4-5	